



OZ SUPER 95 SUPER POLYMER

Design Description

Oz Super 95 has very good values for tensile strength, elongation at break and tear strength. It also has a very low compression set. Its excellent wear resistance, high elasticity, high dynamic resistance as well as low permeability are other advantages. This material is injection molded and also casted available.

Features

- Outstanding toughness & abrasion for high pressure applications
- Mineral oil compatibility is good
- Good resistance to ozone attack & weathering
- High performance polyurethane

Properties	Specified	Unit	Value
Hardness	DIN 53505	Shore A	95 ±2
Hardness	DIN 53505	Shore D	46 ±2
Density	DIN 53479	g/cm ³	1.2
Tensile strength	DIN 53504	N/mm ²	48
Elongation at break	DIN 53504	%	420
Stress ratio 100%	DIN 53504	N/mm ²	17
Stress ratio 300%	DIN 53504	N/mm ²	38
Compression set 20 °C/24h	DIN 53517	%	11
Compression set 70 °C/70h	DIN 53517	%	24
Tear strength	DIN 53515	N/mm	110
Elastic recovery	DIN 53512	%	26
Abrasion	DIN 53516	Mg loss	28
Minimum application temperature		°C	-50
Maximum application temperature		°C	120
Elongation at break after 2000h			420
Storage in distilled water at 95°C			420
Swell in water		%	0.3-0.4 n